

INNOV8 PRODUCTS FZC
Area M6-10
SAIF Zone, Sharjah
United Arab Emirates

Reference: Laboratory Test Report
Lab Identification No. 2424
Invoice No. 28217 (Attached)


One (1) fabric sample, identified as **Blindtex Printex Integral Mesh base cloth**, was received and tested in accordance with the national Fire Prevention Association No. 701, Standard Method of Fire Tests for Flame Propagation of Textiles and Films, (Test 1 Small Scale)". The results are as follows:

Specimen Number	Residual Flame (seconds)	Weight Loss (percent)
1	0.0	12.61
2	0.0	12.16
3	0.0	12.79
4	0.0	07.09
5	0.0	15.08
6	0.0	17.81
7	0.0	15.90
8	0.0	06.80
9	0.0	13.56
10	0.0	10.81
AVG.	0.0	12.46

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds

If there are any questions or we can be of further assistance, please let us know.

Sincerely,



Karon S. Martkins

KSM/ms
Attachment

