

Reference: Laboratory Test Report
Lab Identification No. 1981
Invoice No. 54233 (Attached)


One (1) fabric sample, identified **BLINDTEX WARDTEX WITH INTEGRAL MESH TREATED WITH AEGIS, ANTIMICROBIAL FINISH, FOR CUBICLE CURTAINS, DRAPERIES, VALANCES AND BEDSPREADS**, was received and tested in accordance with the national Fire Prevention Association No. 701, Standard Method of Fire Tests for Flame Propagation of Textiles and Films, (Test 1 Small Scale)". The results are as follows:

Specimen Number	Residual Flame (seconds)	Weight Loss (percent)
1	5.0	19.10
2	0.0	11.95
3	0.0	04.08
4	0.0	13.78
5	0.0	14.10
6	0.0	21.78
7	0.0	22.64
8	0.0	16.36
9	0.0	19.93
<u>10</u>	<u>0.0</u>	<u>17.07</u>
AVG	0.5	16.07

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds

If there are any questions or we can be of further assistance, please let us know.

Sincerely,



Kayon S. Martkins

KSM/ms
Attachment



Reference: Laboratory Test Report

One (1) Fabric sample identified as PATTERN: BLINDTEX WARDTEX INTEGRAL MESH FOR PRIVACY CURTAINS, DRAPERIES, VALANCES AND BEDSPREADS, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2010 Edition, (Test 1, Small Scale)". The results are as follows:

Specimen Number	Residual Flame (seconds)	Weight Loss (percent)
1	0.0	12.61
2	0.0	12.16
3	0.0	12.79
4	0.0	07.09
5	0.0	17.81
6	0.0	15.81
7	0.0	06.80
8	0.0	13.56
9	0.0	10.80
10	0.0	15.08
AVG.	0.0	26.06

The fabric sample submitted meets the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds

If there are any questions or we can be of further assistance, please let us know.

Sincerely,


Karon S. Martkins

KSM/ms
Attachment

